

SEP
2003

1:15 Thinner flashpoints

Thinner	Uses	Flashpoint °C
Mineral turps	Resene Mica Bond Resene Rust-Arrest	38
No.3A	Resene ArmourZinc 125	10
No.4	Resene Vinyl Etch	10
No.5	Resene Armourcote 608 Resene Steel Fab	<0
No.6	Resene Alumastic Resene Armourchlor Series (spray application) Resene Armourcote 210 and 510 Resene ArmourZinc 110 Resene Imperite I.F. 503	24
No.7A	Resene Polymeric AV-8 Resene Uracryl 400 Series (spray application)	50
No.8	Resene Armourcote 221 Resene Uracryl 400 Series (brush/roller application)	42
No.9	Resene Zincilate 10, 10F and 11	29
No.10	Slow Retarder	61
No.11	Resene Armourchlor Series (brush/roller application) Medium Retarder	42
No.12	Resene Armourcote 220 Resene Armourcote 515 Resene ArmourZinc 120 Resene Universal Cleaner	<0
No.13	Resene Imperite 413	4

Resene

the paint the professionals use

*In New Zealand, PO Box 38242, Wellington Mail Centre,
call 0800 RESENE, visit www.resene.co.nz or email advice@resene.co.nz*

*In Australia, PO Box 785, Ashmore City, Queensland,
call 1800 738 383, visit www.resene.com.au or email advice@resene.com.au*